

EPOKOL MIX5

Universal epoxy adhesive

DESCRIPTION EPOKOL MIX5 is a fast curing, two component, solvent free, epoxy adhesive. The joint is translucent, resistant to water, detergents and diluted chemicals. Temperature resistance of joint is between -20°C and +80°C.

FIELDS OF APPLICATION EPOKOL MIX5 is used for gluing metals, glass, stone, ceramics, plastics, wood, plastics (except PE-polyethylene, PP- polypropylene and PTFE- Teflon) etc. It can be used also as a casting resin.

CHARACTERISTICS	A comp.	B comp.
Viscosity at 25 °C (Brookfield):	6 000 – 8 000	10 000 – 18 000
Mixing ratio by volume A : B	1	1
Po life of mixture	approx. 5 minutes	

DANGEROUS GOODS CLASSIFICATION The product is classified as dangerous (see safety data sheet)

APPLICATION The surfaces to be glued must be clean, dry and if possible treated with sandpaper. The glue is than prepared and spread on one surface. Joint both surfaces, keep press and let set for 15 - 20 minutes at the room temperature. The adhesive must be applied in 4-5 minutes. Lower temperatures prolong, higher temperatures speed up the setting time. Gluing below +15°C is not recommended. The final setting is attained in 12 hours.

CLEANING Uncured adhesive can be removed mechanically and cleaned up with hot water and detergent.

PACKING double syringe 27g

STORAGE In well-closed original packing in a dry place at a temperature between +5°C and +25°C. If stored correctly, the adhesive will last at least 18 months.

The information provided herein, especially recommendations for the usage and application of our products, is based on our knowledge, results of laboratory tests and practical experience gained to date.

We guarantee a constant quality of our products under our technical specifications. Technical advice of our application department is available without obligation. This does not release the buyer from testing our products in his own responsibility with respect to their suitability for intended application and application process. Such an evaluation should be repeated if materials are changed in any way or bought from a different source.

We do not accept any liability with regard to above information or with regard to any verbal recommendation since different materials used in conjunction with our products as well as varying working conditions are beyond our control.